



TECHNICAL DATA SHEET

TDS 04.035

Product	CEBOTOP LAK OPACO
Description	Water based finish, based on styrene acrylic resin, odorless, with perfect characteristics of scrub resistance, coverage, whiteness and reduced dirt pick-up. Ideal for residences, offices, public places and wherever the full and rich, smooth and deeply matt finish is requested. CeboTop Lak can be easily matched with precious finishes of the Cebos Color line.
Packaging	CEBOTOP LAK OPACO BIANCO is available in 1 – 3 - 5 -10 LITRES package CEBOTOP LAK OPACO BASE is available in 1- 2,5 - 5 LITRES package
Surface treatment of the substrate	CEBOTOP LAK OPACO can be applied over gypsum, fine renders or previous paintings, perfectly cleaned from eventual dust and incrustations. In case of recently repaired walls, highly absorbent or chalky substrates, apply a coat of priming fixative CeboFix M by brush, diluted 1:1 with water.
Colouring	CEBOTOP LAK can be coloured with CEBOCOLORSTATION tinting system or with CEBOKIT universal colorants in the quantities, indicated on our Colour Cards. If more than one pack has to be produced in the same colour, it is advisable to use bases and colorants carrying the same lot number.
Dilution	10% – 15% with water
Application	CEBOTOP LAK in two coats, with a short hair woollen roller or brush, between the first and the second coat wait minimum 4-6 hours.
Useful suggestions	CEBOTOP LAK can also be applied over metals, wood and plastic: in this case it is necessary to prepare the surface with the appropriate primer.
VOC Classification (2004/42/CE Directive)	Product category: Matt paint for walls and ceilings (a) Maximum VOC content limit value (2010) for the ready-to-use product: 30 g/l. CEBOTOP LAK contains VOC: 29 g/l
Technical characteristics	Estimated coverage: 7-8 m ² /l Appearance: liquid Specific weight CEBOTOP LAK OPACO: BIANCO 1,34 g/cm ³ – BASE 1,29 g/cm ³ pH: 8.5 – 9.5 Drying time: 4-6 hours, between the first and the second coat should pass 24 hours. Specular brilliance angle of measurement 85° classification according to UNI EN ISO 2813-2001 CEBOTOP LAK OPACO 1,6 Gloss VERY MATT Covering power classification according to UNI 11271 CEBOTOP LAK OPACO 97,16% GOOD Dirt pick-up classification according to UNI 10795-1999 CEBOTOP LAK OPACO Delta L 0,64 value of reference < 3 VERY LOW Scrub resistance classification according to UNI 10795-1999 CEBOTOP LAK OPACO relevant value 5500 CYCLES value of reference >5000 CYCLES PERFECT Release of odour classification according to UNI 11021-2002 Appendix A



Cebos Color Srl
24040 Osio Sopra (BG)
Via dei Dossi, 7
Tel. +39 035 265141
Fax +39 035 2651431
C.F. & P.Iva 02567630161
info@cebos.it
www.ceboscolor.it

Review n.1
Date: 21/10/2016

TECHNICAL DATA SHEET

TDS 04.035

CEBOTOP LAK OPACO relevant value 0,2 value of reference <1

Storage

Store the product in its original containers, tightly closed at ambient temperature between +5°C and +35°C, in a cool and well-ventilated place, sheltered from direct sunshine and heat sources.

Safety warnings

CEBOTOP LAK does not require any specific personal or environmental protection measures; it is however advised to avoid long contact with skin. In case of contact with eyes, rinse immediately with plenty of water; if irritations persist seek medical advice. If swallowed, seek medical advice immediately. The users' information is contained in the relative Safety Data Sheet.

This data sheet annuls and substitutes any previous version for this product. All the technical information herein stated come from our best experience: in any case however this Technical Data Sheet does not imply the liability of our Company for application of the product which is carried out beyond our control. Our Technical Department is at the users' service to provide additional information or clarifications.