



TECHNICAL DATA SHEET

TDS 04.030

Product

CEBOGLAM

Description

CEBOGLAM is decorative finish for interiors, based on mineral waxes and precious metallic pigments. CeboGlam is used to enrich classic and modern decorations creating a shiny and metallic glaze for refined and luxury surfaces. In addition to the aesthetic features, the product is water repellent in order to protect and preserve the glamour of the decorations for a long time.

CEBOGLAM is available in four ready bases: Argento (silver), Oro (gold), Oro Rosso (Red gold) and Rame (Copper).

CEBOGLAM is available in 1 litre and 2.5 litres containers for the base Argento and in 1 litre containers for the bases Oro, Oro Rosso and Coppe.

Surface treatment of the substrate

It can be applied over all surfaces finished with CEBOART MARMORINO and perfectly dry. For more information please consult the relative Technical Data Sheet.

Colouring

CEBOGLAM can be coloured with CeboColorStation or with CeboKit universal colorants in the quantities indicated on our Colour Cards. It is also possible to create different shades in addition to those presented on our Colour Cards by varying the quantities or by mixing different colorants. If more than one pack has to be produced in the same colour, it is advisable to use bases and colorants carrying the same lot number.

CeboGlam on CeboArt Stucco application cycle

Apply two coats of CeboArt Stucco with a stainless steel trowel in a uniform layer. The first coat must be dry before the application of the second coat (6-8 hours). The resulting surface must be smooth but not polished. On CeboArt Stucco, perfectly dry and dust-free, apply the first coat of CeboGlam with stainless steel trowel in crossed movements to create the desired decoration. Wait for the first coat of CeboGlam to dry (4-6 hours) and apply the second coat with the same technique. After about two hours, when the product is touch dry, polish the surface with the same trowel to achieve the final brightness

CeboGlam on CeboArt Marmorino application cycle

Apply one coat by crossed movements of CeboArt Marmorino with the stainless steel trowel considering that this step determines the design of the final decoration; before of the complete drying (at least 24 hours), smooth the surface. On the completely dry and dust free CeboArt Marmorino, following its design, apply by crossed movements one coat of CeboGlam with the stainless steel trowel; after the complete drying (at least 4-6 hours), apply in the same way another coat of CeboGlam. After about two hours but before the complete drying to the touch, polish the surface with the stainless steel trowel.

VOC Classification (2004/42/CE Directive)

Product category: Decorative effect coating (I)
Maximum VOC content limit value (2010) for the ready-to-use product:
200 g/l. CEBOGLAM contains: 45 g/l VOC

Technical characteristics

Estimated Coverage: 10 m²/lt
Appearance: liquid
Specific weight: 1.10 – 1.15 g/cm³
pH: 8 - 9
Drying time: 4 – 6 hours between coats. Complete drying after about 24 hours according to ambient temperature and relative humidity.

Storage

Store the product in its original containers, tightly closed at ambient temperature between +5°C and +35°C, in a cool and well-ventilated place, sheltered from direct sunshine and heat sources.



Cebos Color Srl
24040 Osio Sopra (BG)
Via dei Dossi, 7
Tel. +39 035 265141
Fax +39 035 2651431
C.F. & P.Iva 02567630161
info@cebos.it
www.ceboscolor.it

Review n.1
Date: 12/02/2013

TECHNICAL DATA SHEET

TDS 04.030

Safety warnings

CEBOGLAM does not require any specific personal or environmental protection measures; it is however advised to avoid long contact with skin. In case of contact with eyes, rinse immediately with plenty of water; if irritations persist seek medical advice. If swallowed, seek medical advice immediately. The users' information is contained in the relative Safety Data Sheet.

This data sheet annuls and substitutes any previous version for this product. All the technical information herein stated come from our best experience: in any case however this Technical Data Sheet does not imply the liability of our Company for application of the product which is carried out beyond our control. Our Technical Department is at the users' service to provide additional information or clarifications.